This listing of claims will replace all prior versions, and listings, or claims in the application.

Listing of the Claims:

Claims 1-10 (cancelled)

- 11. (Currently amended) A method for the preparation of a crosslinked hydrophilic coating of a hydrophilic polymer on a substrate polymer surface of a medical device, said method comprising the steps of:
- (i) providing a medical device having a substrate polymer surface;
- (ii) providing a polymer solution comprising 1-20% by weight of a hydrophilic polymer, 0-5% by weight of additive(s), and the balance of said solution is comprised of a vehicle having at least one plasticizer with a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen $\delta_{\rm H}$ parameter of less than 20;
- (iii) applying said polymer solution to said substrate
 polymer surface;
 - (iv) evaporating at least a part of the vehicle from said

polymer solution present on said substrate polymer surface; and

(v) curing said hydrophilic polymer, wherein said curing is
the only irradiation step in the process.

- 12. (Previously presented) The method according to claim 11, wherein the polymer solution is applied to said substrate polymer surface in one single application step.
- 13. (Previously presented) The method according to claim 11, wherein the vehicle comprises at least one solvent.
- 14. (Currently amended) The method according to claim 13, wherein the polymer solution consists of: 1-20% by weight of the hydrophilic polymer, 0-5% by weight of additive(s), 1-40% by weight of plasticizer(s), and 50-95% by weight of solvent(s).
- 15. (Previously presented) The method according to claim 11, wherein the substrate polymer is polyurethane.
- 16. (Previously presented) The method according to claim 11, wherein the hydrophilic polymer is polyvinyl pyrrolidone.

Application Serial No. 10/540,108 Attorney Docket No. P70563US0

- 17. (Currently amended) A medical device comprising a substrate polymer surface having thereon a cross-linked hydrophilic coating of a hydrophilic polymer, said medical device being obtained obtainable by the method of claim 11.
- 18. (Previously presented) A medical device comprising a hydrophilic coating of a cross-linked hydrophilic polymer, said coating comprising a hydrophilic plasticizer having a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen $\delta_{\rm H}$ parameter of less than 20.
- 19. (Currently amended) A medical device comprising a hydrophilic coating of a cross-linked hydrophilic polymer, said coating having a hydrophilic plasticizer with a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen δ_H parameter of less than 20, which is said medical device being prepared according to the method of claim 11.
- 20. (Currently amended) The method of use of a polymer solution for the preparation of a cross-linked hydrophilic coating, wherein said polymer solution includes comprises 1-20% by weight

of a hydrophilic polymer, 0-5% by weight of additive(s), and the balance of said solution is comprised of a vehicle having a plasticizing effect on the hydrophilic polymer and including, said vehicle additionally comprising at least one plasticizer having a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen $\delta_{\rm H}$ parameter of less than 20, wherein said method including comprises the steps of:

- (a) applying said polymer solution to said substrate polymer surface;
- (b) evaporating at least a part of the vehicle from said polymer solution present on said substrate polymer surface; and curing said hydrophilic polymer,

wherein said method includes only a single irradiation step.

21. (Previously presented) The method according to claim 15, wherein the hydrophilic polymer is polyvinyl pyrrolidone.